



Prima Cer S.r.l. Unipersonale
Via Ragazzi del 99, 12
41049 Sassuolo (MO)
Tel. +39 0536.813148
Fax +39 0536.888970
C.F. e P.IVA 02729950366
info@primacer.it
Capitale Sociale Euro 11.000,00 i.v.
N. Repertorio Economico Amm. 325941

ALLUMINA IDRATA VENTILATA PIC535-16

Analisi chimica Chemical analysis

| | |
|----------------------------------|----------|
| Al ₂ O ₃ | 65 % |
| Al (OH) ₃ (calcolata) | 99,70 % |
| SiO ₂ | 140 ppm |
| Fe ₂ O ₃ | 180 ppm |
| Na ₂ O | 2100 ppm |
| CaO | 200 ppm |
| P.F. (100-1000C°) | 35,0 % |
| | |
| | |
| | |
| | |
| | |
| | |
| | |

Composizione mineralogica Mineral analysis

| | |
|--|--|
| | |
| | |
| | |
| | |
| | |
| | |
| | |
| | |
| | |
| | |

Granulometria Size

| | |
|-----|-------|
| D50 | 4 µm |
| D90 | 10 µm |
| | |
| | |
| | |
| | |
| | |
| | |
| | |
| | |

Caratteristiche fisiche / Physical Characteristics:

Umidità 1 % max
BET 6 m²/g

Caratteristiche / Characteristics:

Impieghi / Employments:

Note / Notes: