



Prima Cer S.r.l. Unipersonale  
Via Ragazzi del 99, 12  
41049 Sassuolo (MO)  
Tel. +39 0536.813148  
Fax +39 0536.888970  
C.F. e P.IVA 02729950366  
info@primacer.it  
Capitale Sociale Euro 11.000,00 i.v.  
N. Repertorio Economico Amm. 325941

## ALLUMINA CALCINATA PIC537-16

### Analisi chimica Chemical analysis

A l <sub>2</sub> O <sub>3</sub>	99,60 %
S i O <sub>2</sub>	120 ppm
F e <sub>2</sub> O <sub>3</sub>	110 ppm
N a <sub>2</sub> O	3100 ppm
C a O	130 ppm
P.F. (100-1000C°)	0,1 %

### Composizione mineralogica Mineral analysis


### Granulometria Size

D50	55 µm
< 45 µm / 325 mesh	40 %
< 125 µm	95 %

### Caratteristiche fisiche / Physical Characteristics:

B.E.T. 0,6 m<sup>2</sup>/g  
Alpha Allumina 97 %

### Caratteristiche / Characteristics:

### Impieghi / Employments:

### Note / Notes: